

## OVERTURE PC PROFESSIONAL TECHNICAL DATA SHEET

OVERTURE PC PROFESSIONAL has particularly good impact resistance, thermal stability, gloss and flame retardancy, and has a wide temperature range, widely used in the design of electronic product casings.

### Physical Properties (Transparent)

| Property                     | Testing method      | Typical value                       |
|------------------------------|---------------------|-------------------------------------|
| Density                      | ISO 1183, GB/T 1033 | 1.21 (g/cm <sup>3</sup> at 21.5 °C) |
| Vicat Softening temperature* | ISO 306 GB/T 1633   | 115.3 (°C)                          |
| Melt index                   | 210 °C, 2.16 kg     | 10.0 (g/10 min)                     |
| Melting temperature          | DSC, 10°C/min       | N/A                                 |

Tested with 3D printed specimen of 100% infill

### Mechanical Properties (Transparent)

| Property                             | Testing method     | Typical value                  |
|--------------------------------------|--------------------|--------------------------------|
| Young's modulus (X-Y)                | ISO 527, GB/T 1040 | 2253 ± 59 (MPa)                |
| Tensile strength (X-Y)               | ISO 527, GB/T 1040 | 70.2 ± 1.8 (MPa)               |
| Tensile strength (Z)                 | ISO 527, GB/T 1040 | 44.5 ± 0.9 (MPa)               |
| Elongation at break (X-Y)            | ISO 527, GB/T 1040 | 6.7 ± 0.6 (%)                  |
| Bending modulus (X-Y)                | ISO 178, GB/T 9341 | 2588 ± 56 (MPa)                |
| Bending strength (X-Y)               | ISO 178, GB/T 9341 | 93.4 ± 2.1 (MPa)               |
| Notched Charpy impact strength (X-Y) | ISO 179, GB/T 1043 | 5.7 ± 1.4 (kJ/m <sup>2</sup> ) |

All testing specimens were printed under the following conditions:  
 nozzle temperature = 260 °C, printing speed = 45 mm/s, build plate temperature = 95 °C, infill = 100%  
 All specimens were conditioned at room temperature for 24h prior to testing

### Physical Properties (Other filament)

| Property                     | Testing method      | Typical value                       |
|------------------------------|---------------------|-------------------------------------|
| Density                      | ISO 1183, GB/T 1033 | 1.21 (g/cm <sup>3</sup> at 21.5 °C) |
| Vicat Softening temperature* | ISO 306 GB/T 1633   | 110.3 (°C)                          |
| Melt index                   | 210 °C, 2.16 kg     | 7.0 (g/10 min)                      |
| Melting temperature          | DSC, 10°C/min       | N/A                                 |

Tested with 3D printed specimen of 100% infill

## Mechanical Properties (Other filament)

| Property                             | Testing method     | Typical value                   |
|--------------------------------------|--------------------|---------------------------------|
| Young's modulus (X-Y)                | ISO 527, GB/T 1040 | 2138 ± 134 (MPa)                |
| Tensile strength (X-Y)               | ISO 527, GB/T 1040 | 49.8 ± 2.1 (MPa)                |
| Tensile strength (Z)                 | ISO 527, GB/T 1040 | 37.6 ± 1.3 (MPa)                |
| Elongation at break (X-Y)            | ISO 527, GB/T 1040 | 6.2 ± 1.2 (%)                   |
| Bending modulus (X-Y)                | ISO 178, GB/T 9341 | 2293 ± 99 (MPa)                 |
| Bending strength (X-Y)               | ISO 178, GB/T 9341 | 79.8 ± 3.4 (MPa)                |
| Notched Charpy impact strength (X-Y) | ISO 179, GB/T 1043 | 20.5 ± 0.9 (kJ/m <sup>2</sup> ) |

All testing specimens were printed under the following conditions:  
 nozzle temperature = 260 °C, printing speed = 45 mm/s, build plate temperature = 95 °C, infill = 100%  
 All specimens were conditioned at room temperature for 24h prior to testing

## Recommended Printing Conditions

|                                 |  |
|---------------------------------|--|
| <b>Nozzle temperature</b>       | 250 - 270 (°C)                               |
| <b>Build surface material</b>   | OVERTURE Build Surface, Textured PEI         |
| <b>Build surface treatment</b>  | None, Applying PVA glue to the build surface |
| <b>Build plate temperature</b>  | 90-105 (°C)                                  |
| <b>Cooling fan</b>              | Turned off                                   |
| <b>Printing speed</b>           | 30-50 (mm/s)                                 |
| <b>Raft separation distance</b> | 0.1-0.2 (mm)                                 |
| <b>Retraction distance</b>      | 1-3 (mm)                                     |
| <b>Retraction speed</b>         | 20-40 (mm/s)                                 |
| <b>Threshold overhang angle</b> | 45 (°)                                       |

Based on 0.4 mm nozzle.  
 Printing conditions may vary with different nozzle diameters

## Disclaimer

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End- use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice.

Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/recycling practices of OVERTURE materials for the intended application. OVERTURE makes no warranty of any kind, unless announced separately, to the fitness for any use or application. OVERTURE shall not be made liable for any damage, injury or loss induced from the use of OVERTURE materials in any application.